

ZYGLO®

ZYGLO® ZL-27A

Level 3 Post Emulsifiable Fluorescent Penetrant

General Description

Post-emulsifiable ZL-27A is a Level 3, high-sensitivity Type-1 penetrant designed for inspections which require maximum process control and reliability, such as safety-critical aerospace testing.

Since ZL-27A is not water soluble, there is minimal risk of this penetrant being removed from a fine or shallow defect through over-washing to provide the highest reliability of any penetrant inspection method.

ZL-27A has a high flash point and provides long tank life when used in open dip tanks, but this penetrant can also be applied in a variety of other ways, including electrostatic spray.

To remove surface ZL-27A penetrant before developer application, use ZE-4E Method B lipophilic emulsifier or ZR-10E Method D hydrophilic emulsifier can be used.

ZL-27A is listed on the QPL SAE AMS 2644 Qualified Product List and is approved for use by Pratt & Whitney.

Benefits

Improve indication detection

- Clear, bright indications are easier to detect due to high UV and thermal stability – even for small flaws and discontinuities
- Indications stand out more since background fluorescence is minimized; emulsifiers only remove surface penetrant without the risk of over-washing

Maximize penetrant inspection Process control

- Prevents over-washing since ZL-27A cannot be removed with water (unless it combines with an emulsifier)
- PE penetrant system is less susceptible to human error since only surface penetrant is removed in the final rinse stage

Wide Range of inspections

- Inspect a wide range of high-value components without fear of corrosion or specification non-conformance
- Meets all major industry and NDT specification requirements, including Aerospace Prime and OEM specs, AMS 2644 and ISO 3452

Maximize operator comfort and safety

- Promotes better inspection quality by providing the operator with a more comfortable work environment
- Reduces discomfort from strong odors
- Exceeds all EHS requirements



Specification compliance

- AECL
- AMS 2644
- ASME BPVC
- ASTM E1417
- ASTM E165
- Boeing BAC 5423 PSD 6-46 or 8-4
- Boeing PS-21202
- ISO 3452
- MIL-STD-2132
- MIL-STD-271
- NAVSEA T9074-AS-GIB-010/271
- Pratt & Whitney PMC 4353
- QPL SAE AMS 2644

Typical Properties (not specification)

Flash Point	> 200°F / 93°C
Density	0.96 g/cc / 7.72 lb/gal (926 g/L)
Viscosity (at 100°F / 38°C)	9.65 cs
NPE-Free	Yes

ZYGLO®

USE RECOMMENDATIONS

NDT Method	Penetrant Testing Fluorescent
Method(s)	B/C/D
Type	1
Sensitivity Level	3, High sensitivity
Usage Temperature	40 to 125°F / 5 to 52°C
Storage Temperature	50 to 86°F/10 to 30°C
Coverage	1 gal will cover approximately 1,000 ft ² / 93 m ²

PACKAGING

Aerosol	F02011
20 Liters	F02009
205 Liters	F02010

HEALTH AND SAFETY

Review all relevant health and safety information before using this product. For complete health and safety information, refer to the product Safety Data Sheet, which is available at www.magnaflux.in

APPLICATIONS

Defect location: open to surface
Ideal for:

- Detecting fine discontinuities
- Critical components
- Precision castings
- Precision forgings
- Machined components
- Immersion dip tank
- Electrostatic spray

Defect examples: Fine Cracks, Seams, Porosity

FEATURES

- Level 3 high sensitivity
- Post emulsifiable
- Bright indications
- Resists over-washing or over-removal
- High flash point
- Wide range of application methods
- Low odor
- Very low toxicity
- Alloy compatibility
- High thermal resistance
- High UV stability
- QPL SAE AMS 2644 Qualified Product List
- Approved for use by Pratt & Whitney

MAGNAFLUX,
DIVISION OF ITW INDIA PRIVATE LIMITED,
Plot No: 51,52, 207 & 208, Phase – 2, IDA,
TGIIC, Pashamlaram, Medak Dist.-502307,
Telangana State, India
Tel: +91 8455 224710 Fax: +91 8455 224709
Email: magnafluxinfo@magnafluxindia.com
www.magnaflux.in

